



Zinc AnOde alloy cOmpOsiTiOn	
Element	Wt%
Aluminum	0.0055 Max
Cadmium	0.03 Max
IrOn	0.0014 Max
Zinc	Remainder

INGOT WEIGHT: 12LBS.

NOTES:

- ANODE SOAKING REQUIREMENTS:  
PLACE ANODE IN HOLE OR TRENCH. ADD 5 GALLONS OF WATER AND ALLOW TO SOAK FOR 30 MIN. BACKFILL TO TOP OF ANODE. ADD AN ADDITIONAL 5 GALLONS OF WATER TO COMPLETELY SATURATE THE SOIL SURROUNDING ANODE. LET SOAK FOR 15 MIN. COMPLETE BACKFILLING PROCESS PER MNWD STD. SPECIFICATION SECTION 02223.

MOULTON NIGUEL WATER DISTRICT  
ZINC ANODE FOR SERVICES  
& AIR-VACS

DRAWING  
NUMBER

W-29